



TRE EMME S.p.A.
MANIFATTURA MARCHIGIANA MACERATA
Via Dell'Artigianato, 22
62020 S. ANGELO IN PONTANO (MC) - ITALY
Iscr. Reg. Soc. MC N. 5227 - CCIAA MC N. 100692
Tel. +39 0733.663334/663316/663416 - Fax +39 0733.663417
CAP. SOC. Euro 120.000,00 - P. IVA 00860500438
<http://www.treemme.net> - e-mail: treemme@treemme.net
V.A.T. reg. IT 00860500438

TECHNICAL REPORT SHEET

Barrier tape white/red

Test	Method	Unit	AVG Values
Grammage	ISO 4591	g/m ²	21 +/-5%
Thickness of the film	PLT01	my	25 +/- 5%
Tensile Strength at Peak MD	ASTM D882	N/Inch	20
Tensile Strength at Peak CD	ASTM D882	N/Inch	12
Load at 10% Elongation MD	ASTM D882	N/Inch	10
Load at 10% Elongation CD	ASTM D882	N/Inch	9
Elongation at Break MD	ASTM D882	%	300
Elongation at Break CD	ASTM D882	%	400
Tread Level Outside of the Roll	ASTM D2578	Dyne/cm	≥39
COF	ASTM D1894	-	<0,35

The information submitted in this sheet is based on our current knowledge and experience, therefore these data serve as general information only.

Rev.02 on 16-04-2018